



CHARACTERISTICS

CROSONE 325 is a sealer and applied with a spatula or trowel. Its formulation is based on a acrylic emulsion that provides a variety of acoustic and non acoustic structures. The product is designed to get an optimal sealing with spatula and trowel application in sound installations.

SPECIFICATIONS

| | |
|-------------------------|--|
| Material | Heavy acrylic emulsion. |
| Colour | Gray. |
| Density | 1,83 kg/l. |
| Solvents | Free. |
| Tack time | 30 minutes at 20 °C. |
| Crosslinking rate | 1 mm every 24 hours at 20 °C. |
| Application temperature | From 5 °C to 40 °C. |
| Working temperature | From – 20 °C to 80 °C. |
| Movement accommodation | 15 % the width of the board. |
| Joint size | 12 mm depth of the same. Maximum width 25 mm. |
| Shore hardness A | 25. |
| Breaking load | 0.8 Mpa. |
| Elongation at break | 230 %. |
| Presentation | 25 kg. Plastic pail. |
| Palet | 36 Pails (900 kgs). |

PROPERTIES

CROSONE 325 has the following advantages:

- It's a good acoustical sealant
- Easy to apply.
- Flexibility permanent.
- Waterproof, dustproof and waterproof.
- Once the ice lattice is unchanged.
- Outstanding adhesion.
- Absorbs structural movement without cracking.
- Open time prolonged.

APPLICATIONS

Crosone 325 is a product for sealing low movement joints and to reduce noise transmission through them. It is used in walls, partitions and other structures and to avoid sound bridges the perimeter sealing of pipes and cables as they pass through walls and ceilings. It is also suitable for sealing perimeter doors and windows firewall and acoustic.

HOW TO USE

Crosone 325 is affixed to all kinds of commonly used building elements, such as brick, mortar, concrete, PVC pipe, glass, wood, etc.

The surface must be clean, dry and degreased, not containing bad adherence.

Crosone 325 is applied by trowel or spatula.

For fixing polystyrene partitions apply to peltate.

| Crosone 325 consumption | | | | | | |
|-------------------------|-------|-------|-------|-------|-------|-------|
| Width (cm) | 1 | 1,5 | 2 | 3 | 4 | 5 |
| Depth (cm) | 1 | 1,5 | 2 | 3 | 4 | 5 |
| Length (cm) | 100 | 100 | 100 | 100 | 100 | 100 |
| Consumption kg/ml | 0,183 | 0,411 | 0,732 | 1,395 | 2,927 | 4,575 |

PRECAUTIONS

CROSONE 325 manipulation does not require special security measures.

We suggest cleaning tools with water immediately after use.

The product in contact with the eyes should be washed with clean water. If the discomfort persists require medical assistance.

Not recommended for use with bitumen or asphalt.

Do not use it on materials that can be distilled oils or solvents.

Do not use in joints that are permanently submerged.

We recommend testing for compatibility of product with the surfaces to be treated.

Information in this document and otherwise supplied to users is based on our general experiences and is given in good faith but, because of particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or implied with respect to such information. Specifications are subject to change without notice.

CROXON, S. L.

Polig. Ind. Majaravique, 27 B
41309 La Rinconada (Sevilla)

Tel.: +34 954 904 225

Fax: +34 954 906 676

E-mail: croxon@croxon.es

Web: www.croxon.es